

**LOCTITE®**



# LOCTITE® 3D IND408™

High Modulus Black  
Photoplastic Resin for SL

**LOCTITE®**

Henkel Corporation

[loctite3dp@henkel.com](mailto:loctite3dp@henkel.com)



# LOCTITE®

**IND408™**  
HIGH MODULUS  
BLACK



## PROPERTIES

Mechanical Properties	Measure	Method	Post Processed
Tensile Stress at Break	MPa	ASTM D638	42 ± 3 <sup>[1]</sup>
Young's Modulus	MPa	ASTM D638	3240 ± 80 <sup>[1]</sup>
Elongation at Break	%	ASTM D638	1,3 ± 0,1 <sup>[1]</sup>
Flexural Stress at Break	MPa	ASTM D790	144 ± 5 <sup>[2]</sup>
Flexural Modulus	MPa	ASTM D790	3830 ± 40 <sup>[2]</sup>
IZOD Impact (Notched)	J/m	ASTM D256	16 ± 1 <sup>[3]</sup>
Shore Hardness	D	ASTM D2240	80 <sup>[8]</sup>

Thermal Properties	Measure	Method	Post Processed
HDT at 0.46 MPa	°C	ASTM D648	118 ± 1 <sup>[4]</sup>
HDT at 1.82 MPa	°C	ASTM D648	95 ± 3 <sup>[4]</sup>

Other Properties	Measure	Method	Post Processed
Viscosity at 25°C	cP	ASTM D7867	200 <sup>[6]</sup>
Water Absorption (24 h)	%	ASTM D570	0.4 <sup>[5]</sup>
Water Absorption (7 days)	%	ASTM D570	0.9 <sup>[5]</sup>
Liquid Density	g/cm <sup>3</sup>	ISO 1675	1.1 <sup>[7]</sup>
Ec	mJ/cm <sup>2</sup>	Internal	9,0
Dp	mil	Internal	6.4

\*All specimen are printed unless otherwise noted. All specimen were conditioned in ambient lab conditions at 19-23°C / 40-60% RH for at least 24 hours.\* ASTM Methods: D638 Type IV, 5 mm/min, D790-B, 1.5 mm/min, D648, D256 Notched IZOD (Machine Notched), 6 mm x 12 mm, D570 0.125" x 2" Disc 24hr@ 25°C, D2240, Type "D" (0, 3 seconds), D7867

**Internal Data Sources:**

[1] FOR51764, [2] FOR51766, [3] FOR51768, [4] FOR51762, [5] FOR51774, [6] FOR51480, [7] FOR54345 [8] FOR57401



# LOCTITE®

**IND408™**  
HIGH MODULUS  
BLACK



## PRINTING

To achieve the properties provided the material was printed on a 355nm laser SL printer.

## POST PROCESSING

LOCTITE 3D IND408 BK requires post processing to achieve specified properties. Prior to post curing support structures should be removed from the printed part and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

Post Process Step	Agent	Method	Duration	Intervals	Additional Info
Cleaning	IPA	e.g. orbital shaker	2 min	1	
Dry	n.a.	Compressed air	10 to 60 s	1	Air pressure (50 psi)
Wait before post curing	n.a.	Ambient condition	60 min	1	Room temperature

## POST CURING

LOCTITE 3D IND408 BK requires post curing to achieve specified properties. It is recommended that a wide spectrum lamp be used to post cure parts.

LOCTITE 3D IND408 BK requires a thermal curing cycle after UV post curing to achieve specified properties. It is recommended to place parts in a pre-heated oven to cure the parts at 140°C for 1h.



# LOCTITE®

**IND408™**  
HIGH MODULUS  
BLACK



## NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of **Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark Usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

